


- ❖ Polymers
- ❖ Chemicals & Aromatics
- ❖ Fuel & Feeds Stock

TITANIUM DIOXIDE R5566

Quality Index	Index	Result		
TiO₂ Content	93.0	95.3	95.3	95.3
Brightness	94.00	94.8	94.9	94.8
Scattering Power	1900	1994	1992	1993
Moisture	0.5	0.3	0.3	0.3
PH Value	6.5 – 8.5	7.1	7.0	7.1
Oil Absorption	23	17	17	17
Sieve Residue	0.015	0.01	0.01	0.01
Specific Resistance	40	169	189	164
Content of Rutile	97	98.6	98.8	98.7
Result : Qualified by the test of DFT/QC-R-053				

تهران: خیابان ملاصدرا، خیابان شیخ بهایی جنوبی، خیابان برزیل غربی، پلاک ۱۴۰، طبقه ۴، واحد ۱۶

+98 21 86017285 

info@elsapaco.com 
www.elsapaco.com 